



TECHNICAL DATA SHEET

STOEP PAINT

1. PRODUCT DESCRIPTION

Stoep Paint is a traditionally formulated alkyd based, interior, gloss floor coating for domestic high traffic areas that need a highly washable, alkali and abrasion resistant coating.

It is available in a range of colours.

2. Application Areas

- Dry (15% maximum moisture level) cement floors
- Primed metal and wooden substrates

3. Product Features

- Highly washable
- Humidity and abrasion resistant
- Excellent adhesion to a range of properly prepared, dry flooring substrates
- Excellent, no-mess application properties
- Excellent flow and levelling
- High hiding power and film
- Alkali-resistant when applied to dry cement floors (15% maximum moisture level)

Drying Time

Allow 18-24 hours (but not more than 48 hours) to dry, and then recoat.

Film Thickness

30 microns per coat

Spreading Rate,

the spreading rate will vary with porosity and type of substrate. For uncoated new work 1 litre will cover about 6-8m². For subsequent coats and when applied to sealed or previously painted substrates, 1 litre will cover 8-10m².

4. Application Details

- Mixing

- Always stir well before use with a flat paddle.
- Mix the epoxy base with the polyamide curing agent in the correct ratio, i.e. 4:1 (4 parts epoxy bases to 1-part polyamide curing-agent). Mix for 5–10 minutes.



PROTECTION WHERE YOU NEED IT!

Limitation of liability applies. Refer to annexure for full disclosure.
April 2009 - INDUSTRIAL RANGE - HB EPOXY PIPE COAT - revision 1 of 2009.



· Application Method

· Use a brush, mohair roller or airless spray to apply a generous coat of Pro-Paint Stoep Paint Enamel to the area that needs protecting.

- Thinning
- Cleaning
- Application

- No thinning is required.
- Clean application equipment with White Spirits
- Stir well before use.
- Use a brush or mohair roller to apply a generous coat of Pro-Paint Stoep Paint Enamel.
- Allow 18-24 hours to dry before recoating.
- Use a brush or roller to apply a second generous coat.

5. Surface Preparation

· Rusted Metal

· Affected areas need to be cleaned back to bright metal and spot primed with Pro-Paint Water based Metal/Galvanized Primer.

· New Metal

· Surfaces need to be abrasively degreased to remove the manufacturer's grease protective layer.
· This process is repeated until the surface is water break free. After drying, the whole substrate is coated with Pro-Paint Water based Metal/Galvanized Primer

· Previously Painted Surfaces

· Remove all loose, flaking or bubbling paint. Remove all dust, foreign material or fungal and algal growth. Allow to dry. Spot prime with Pro-Paint Stoep Paint thinned with 5 % Pro-Paint White Spirits.

· Dry (maximum moisture 15%)

· Remove all dust, foreign material or fungal and algal growth. Fill and seal all visible cracks with a suitable flexible sealant.

6. Colour Range and QTY's

- Available in red oxide, grey, brilliant green and black
- Available in 500m; 1 / 5 / 20 litres

7. Precautions

- This material is highly flammable.
- Flashpoint is 37°C.
- Apply only in ventilated areas, away from ignition sources



PROTECTION WHERE YOU NEED IT!

Limitation of liability applies. Refer to annexure for full disclosure.
April 2009 - INDUSTRIAL RANGE - HB EPOXY PIPE COAT - revision 1 of 2009.



8. Disclaimer

The recommendations contained herein are given in good faith and are meant to guide the specifier or the user. They are based on results gained from our experiences and tests and are believed to be reliable. No guarantee is implied by the recommendations contained herein since conditions of use, method of application and cleanliness of the substrate prior to painting are beyond our control. Pro-Paint (Pty) Limited accept no responsibility or accountability for either the workmanship in surface preparation or the application of our products. Should the reader wish to use the general specification for a PARTICULAR project, then he should first confirm with our Technical Service Department that the specification can be used. NB: IT IS THE RESPONSIBILITY OF THE USER TO ENSURE THAT THE LATEST TDS IS BEING USED, AND THAT IT HAS NOT BEEN SUPERSEDED. We cannot take any responsibility where this precaution has not been taken.



PROTECTION WHERE YOU NEED IT!

Limitation of liability applies. Refer to annexure for full disclosure.
April 2009 - INDUSTRIAL RANGE - HB EPOXY PIPE COAT - revision 1 of 2009.