



PRODUCT DATA SHEET

INDUSTRIAL RANGE

URETHANE – FLOOR COATING SYSTEM

1. DESCRIPTION

A high quality Urethane finish based on modified Alkyd resins.

2. PRINCIPAL CHARACTERISTICS

- Recoatable urethane finish in the SUPERIOR RANGE.
- Suitable for internal / external cement and concrete floors.
- Suitable for normal and high humidity (maximum 95%) atmospheric conditions.
- Will cure at low ambient temperatures.
- Good application properties and can be over coated with conventional paints.
- Good adhesion on most aged, sound alkyd- and epoxy coatings.

3. PACKAGING, COLOURS AND GLOSS

- 1lt and 5lt
- Standard colours: Grey, green , black, red oxide.
- Semi gloss finish.

4. BASIC DATA AT 23°

- | | |
|--------------------------|---|
| • Drying time: | ± 2hrs surface dry.
± 18Hrs full cure. |
| • Recoating time: | ± min 4hrs for 100µm dft, max unlimited. |
| • Pot life: | ± N/a. |
| • Induction period: | ± 15min – 20min. |
| • Mass relative density: | ± 1.0– 1.1 g/cm ³ . |
| • Solids by volume: | ± 49%. |
| • Viscosity: | ± 80 – 85Ku |
| • Recommended dft: | 100µm per coat. (2 coats recommended.) |



PROTECTION WHERE YOU NEED IT!

Limitation of liability applies. Refer to annexure for full disclosure.
April 2009 - INDUSTRIAL RANGE - HB EPOXY PIPE COAT - revision 1 of 2009.



- Theoretical spreading rate: 6 – 8m²/lt for 100µm.
- Practical spreading rate: 5 – 7m²/lt for 100µm.
- Shelf life: at least 12 months in cool and dry conditions.
- Flash point: base 25°C.

5. RECOMMENDED SUBSTRATE CONDITIONS AND TEMPERATURES

- The substrate must be free from any contamination and sufficiently abraded if necessary.
- The substrate must be dry before and during application of URETHANE FLOOR COAT.
- Substrate temperature should be between 10°C and 30°C and at least 3°C above dew point during application and curing.
- Maximum relative humidity during application and curing is 95%.

6. INSTRUCTIONS FOR USE

- Stir well before use.
- Product temperature of the mixed base should be above 15°C to achieve application viscosity.
- Mineral Turpentine can be introduced to lower the viscosity if necessary. Do not exceed 10% to volume.
- Too much solvent will reduce sag resistance and opacity.
- Always ensure adequate ventilation.

- AIRLESS SPRAY:
- Recommended thinner: Mineral Turpentine.
- Volume of thinner: Thinning not recommended.
- Nozzle orifice: ± 0.46 – 0.53mm.
- Nozzle pressure: 13 – 16MPa (± 130 to 160 bar).

- AIR SPRAY:
- Recommended thinner: Mineral Turpentine.
- Volume of thinner: 0 – 5%, depending on required thickness and application conditions.
- Nozzle orifice: ± 1.5 – 2mm.
- Nozzle pressure: 0.3 – 0.4MPa (± 3 to 4 bar).

- BRUSH / ROLLER: (not recommended)
- Recommended thinner: Mineral Turpentine.
- Volume thinner: 0 – 5%, depending on required thickness and application conditions.
- Cleaning solvent: Mineral Turpentine.



PROTECTION WHERE YOU NEED IT!

Limitation of liability applies. Refer to annexure for full disclosure.
April 2009 - INDUSTRIAL RANGE - HB EPOXY PIPE COAT - revision 1 of 2009.



7. SAFETY PRECAUTIONS

This is a solvent based paint, avoid inhalation of spray mist vapour as well as contact between the wet paint and exposed skin or eyes.



PROTECTION WHERE YOU NEED IT!

Limitation of liability applies. Refer to annexure for full disclosure.
April 2009 - INDUSTRIAL RANGE - HB EPOXY PIPE COAT - revision 1 of 2009.