



PRODUCT DATA SHEET

INDUSTRIAL RANGE

QUICK DRY RED OXIDE PRIMER

1. DESCRIPTION

High quality zinc phosphate primer, based on modified short oil alkyd resin.

2. PRINCIPAL CHARACTERISTICS

- Good adhesion properties on new un-rusted steel.
- Fast drying.
- Fast hardening.
- Recoat able with conventional one component coatings.
- Not suitable for immersion in water.

3. PACKAGING, COLOURS AND GLOSS

- 1lt, 5lt, 20lt and 200lt.
- Red oxide.
- Matt.

4. BASIC DATA AT 23°

- | | |
|-------------------------------|--|
| • Drying time: | ± 20min surface dry.
± 3hrs hard dry. |
| • Recoating time: | ± min 3hrs for 40µm dft, max unlimited. |
| • Mass relative density: | ± 0.95 – 0.97 g/cm ³ . |
| • Solids by volume: | ± 63%. |
| • Viscosity: | ± 50 – 60sec. |
| • Recommended dft: | 40µm per coat. (2 coats recommended.) |
| • Theoretical spreading rate: | 14 - 18m ² /lt for 40µm. |
| • Practical spreading rate: | 6 – 8m ² /lt for 40µm. |
| • Shelf life: | at least 12 months in cool and dry conditions. |



PROTECTION WHERE YOU NEED IT!

Limitation of liability applies. Refer to annexure for full disclosure.
April 2009 - INDUSTRIAL RANGE - HB EPOXY PIPE COAT - revision 1 of 2009.



- Flash point: 15°C - 25°C.

5. RECOMMENDED SUBSTRATE CONDITIONS AND TEMPERATURES

- Steel; unpainted, dry and free from any surface contamination.
- Substrate temperature should be between 10°C and 30°C and at least 3°C above dew point during application and curing.
- Ambient temperature between 5°C and 40°C with a maximum relative humidity of 85%.

6. INSTRUCTIONS FOR USE

- Stir well before use.
- Product temperature should be above 15°C to achieve application viscosity.
- Quick dry thinners can be introduced to lower the viscosity if necessary. Do not exceed 10% to volume.
- Too much solvent will reduce sag resistance.
- Always ensure adequate ventilation.

• AIRLESS SPRAY:

- Recommended thinner: QD Thinners.
- Volume of thinner: 0 – 10%, depending on required thickness and application conditions.
- Nozzle orifice: ± 0.38 – 0.48mm.
- Nozzle pressure: 12 – 16MPa (± 120 to 160 bar).

• AIR SPRAY:

- Recommended thinner: QD Thinners.
- Volume of thinner: 0 – 10%, depending on required thickness and application conditions.
- Nozzle orifice: ± 1.8 – 2mm.
- Nozzle pressure: 0.35MPa (± 3½ bar).

• BRUSH / ROLLER: (not recommended)

- Recommended thinner: QD Thinners.
- Volume thinner: 0 – 5%, depending on required thickness and application



PROTECTION WHERE YOU NEED IT!

Limitation of liability applies. Refer to annexure for full disclosure.
April 2009 - INDUSTRIAL RANGE - HB EPOXY PIPE COAT - revision 1 of 2009.



- Cleaning solvent:

conditions.
QD Thinners.

7. SAFETY PRECAUTIONS

This is a solvent based primer, avoid inhalation of spray mist vapor as well as contact between the wet paint and exposed skin or eyes



PROTECTION WHERE YOU NEED IT!

Limitation of liability applies. Refer to annexure for full disclosure.
April 2009 - INDUSTRIAL RANGE - HB EPOXY PIPE COAT - revision 1 of 2009.