



PRODUCT DATA SHEET

INDUSTRIAL RANGE

QUICK DRY ETCH COAT PRIMER

1. DESCRIPTION

High quality zinc phosphate primer, based on modified PVB Phenol alkyd resin.

2. PRINCIPAL CHARACTERISTICS

- Anticorrosive properties.
- Fast drying.
- Fast hardening.
- Recoat able with one and two component coatings.
- Not suitable for immersion in water.

3. PACKAGING, COLOURS AND GLOSS

- 1lt, 5lt and 20lt.
- Black, grey and red oxide.
- Matt.

4. BASIC DATA AT 23°

- Drying time: ± 30 min surface dry.
 ± 5 hrs hard dry.
- Recoating time: \pm min 3hrs for 40 μ m dft, max unlimited.
- Mass relative density: $\pm 0.95 - 0.97$ g/cm³.
- Solids by volume: $\pm 17\%$.
- Viscosity: $\pm 30 - 50$ sec.
- Recommended dft: 40 μ m per coat. (2 coats recommended.)
- Theoretical spreading rate: 3m² - 5m²/lt for 40 μ m.
- Shelf life: at least 12 months in cool and dry conditions.
- Flash point: 28°C.



PROTECTION WHERE YOU NEED IT!

Limitation of liability applies. Refer to annexure for full disclosure.
April 2009 - INDUSTRIAL RANGE - HB EPOXY PIPE COAT - revision 1 of 2009.



5. RECOMMENDED SUBSTRATE CONDITIONS AND TEMPERATURES

- Steel; unpainted, dry and free from any surface contamination.
- Substrate temperature should be between 10°C and 30°C and at least 3°C above dew point during application and curing.

6. INSTRUCTIONS FOR USE

- Stir well before use.
- Product temperature of the stirred base should be above 15°C to achieve application viscosity.
- Quick dry thinners can be introduced to lower the viscosity if necessary. Do not exceed 10% to volume.
- Too much solvent will reduce sag resistance.
- Always ensure adequate ventilation.

- AIRLESS SPRAY:

- Recommended thinner: QD Thinners.
- Volume of thinner: 0 – 10%, depending on required thickness and application conditions.
- Nozzle orifice: ± 0.38 – 0.48mm.
- Nozzle pressure: 12 – 16MPa (± 120 to 160 bar).

- AIR SPRAY:

- Recommended thinner: QD Thinners.
- Volume of thinner: 0 – 10%, depending on required thickness and application conditions.
- Nozzle orifice: ± 1.8 – 2mm.
- Nozzle pressure: 0.35MPa (± 3½ bar).

- BRUSH / ROLLER: (not recommended)

- Recommended thinner: QD Thinners.
- Volume thinner: 0 – 5%, depending on required thickness and application conditions.
- Cleaning solvent: QD Thinners.



PROTECTION WHERE YOU NEED IT!

Limitation of liability applies. Refer to annexure for full disclosure.
April 2009 - INDUSTRIAL RANGE - HB EPOXY PIPE COAT - revision 1 of 2009.



7. SAFETY PRECAUTIONS

This is a solvent based paint, avoid inhalation of spray mist vapor as well as contact between the wet paint and exposed skin or eyes.



PROTECTION WHERE YOU NEED IT!

Limitation of liability applies. Refer to annexure for full disclosure.
April 2009 - INDUSTRIAL RANGE - HB EPOXY PIPE COAT - revision 1 of 2009.